

# **International Journal of Food Properties**



ISSN: (Print) (Online) Journal homepage: https://www.tandfonline.com/loi/ljfp20

# Bio-based smart materials for fish product packaging: a review


Alemu Lema Abelti, Tilahun Abera Teka, Sirawdink Fikreyesus Forsedo, Metekia Tamiru, Geremew Bultosa, Ashraf Alkhtib & Emily Burton

To cite this article: Alemu Lema Abelti, Tilahun Abera Teka, Sirawdink Fikreyesus Forsedo, Metekia Tamiru, Geremew Bultosa, Ashraf Alkhtib & Emily Burton (2022) Bio-based smart materials for fish product packaging: a review, International Journal of Food Properties, 25:1, 857-871, DOI: 10.1080/10942912.2022.2066121

To link to this article: <a href="https://doi.org/10.1080/10942912.2022.2066121">https://doi.org/10.1080/10942912.2022.2066121</a>









## Bio-based smart materials for fish product packaging: a review

Alemu Lema Abelti<sup>a,b</sup>, Tilahun Abera Teka<sup>b</sup>, Sirawdink Fikreyesus Forsedo<sup>b</sup>, Metekia Tamiru<sup>c</sup>, Geremew Bultosa<sup>d</sup>, Ashraf Alkhtib<sup>e</sup>, and Emily Burton<sup>e</sup>

<sup>a</sup>Batu Fish and other Aquatic Life Research Center, Oromia Agricultural Research Institute, Batu, Ethiopia; <sup>b</sup>Department of Postharvest Management, College of Agriculture and Veterinary Medicine, Jimma University, Jimma, Ethiopia; Department of Animal Science, College of Agriculture and Veterinary Medicine, Jimma University, Jimma, Ethiopia; <sup>d</sup>Department of Food Science and Technology, Botswana University of Agriculture and Natural Resources, Gaborone, Botswana; eNottingham Trent University, School of Animal, Rural and Environmental Sciences, Brackenhurst Campus, Southwell, UK, NG25 0QF

#### **ABSTRACT**

Conventional packaging offers protection, containment, communication, and convenience to packaged food. The most commonly used packaging materials are petrochemical-based plastics which generate massive wastes that persist for a long time in the environment after their use. Bio-based materials are the best option to replace this synthetic plastic. This review presents the importance of packaging fish products using polysaccharides, proteins, polyhydroxyalkanoates, polylactic acids, pullulan, and xanthan gums loaded with different nanofillers and bioactive molecules. Bio-based smart materials easily decompose into carbon dioxide, methane, water, and inorganic compounds. Biopolymers can be produced from natural biomass, bio-monomers, and microorganisms. These biopolymers demonstrate excellent physiochemical, thermal, and mechanical properties when mixed or alone as fish packaging materials. Integration of nanofillers and bioactive molecules improves mechanical, gas barrier, antioxidant and antimicrobial properties of bio-based materials. Bioactive molecules like anthocyanins, betalains, curcumin, and clove oil are sensitive to pH, temperature, light, and time. Bioactive molecules can be loaded into bio-based packaging materials to monitor the real-time freshness of fish products during storage. It is concluded that bio-based smart materials have the potential for fish packaging, do not harm the environment, and easily interact with nanofillers and bioactive molecules.

#### **ARTICLE HISTORY**

Received 19 November 2021 Revised 1 April 2022 Accepted 10 April 2022

#### **KEYWORDS**

Bioactive molecules; biopolymers; Fish packaging; nanofillers

#### Introduction

Globally 179 million tons of fish were produced from captured fisheries and aquaculture in 2018.<sup>[1]'</sup> Fisheries play an important role in food security and create job opportunities for 59.5 million people across the world.<sup>[2]</sup> With business-as-usual practices in Africa, the fish sector was estimated to create 20.7 million jobs by 2030 with an annual value of 3.3 billion USD. [3] Fish is an excellent source of proteins, omega-3 fatty acids, calcium, phosphorus, iron, zinc, magnesium, vitamin A and iodine. [4] However, fish products are highly perishable and need to be preserved in appropriate packaging for handling, distribution, and export. [5] Plastic is the principal food-packaging material. Most (70%) of plastics wastes is generated from food packaging. [6] Plastics are durable, cheap, strong, a good barrier to moisture, light, and highly processable into different shapes. However, the utilization of synthetic plastics leads to dispute as it resulted in depletion of petroleum reserves, global warming, and environmental

CONTACT Alemu Lema Abelti alemulema2010@gmail.com Department of Postharvest Management, College of Agriculture and Veterinary Medicine, Jimma University, Jimma, Ethiopia

pollution.<sup>[7]</sup> The usage of petrochemical-based packaging materials is a risk to environmental safety and human health. Moreover, synthetic plastics are hardly recycled or have limited recyclability. Even though pyrolysis and hydrothermal processing convert plastic waste into fuel, its application is limited due to the emission of toxic gaseous during high-temperature combustion of plastics.<sup>[8]</sup> In recent years, enzymatic and microbial biodegradation of synthetic plastics has started but the possibility to apply biological treatment is limited due to the difficulty in adhering and colonizing microbes on the surface of plastics. Generally, recycling, landfilling, and incineration are ineffective for the management of plastic wastes. [9] The prevailing environmental pollution has pushed to explore sustainable packaging. [10] An alternative option to this synthetic plastic is biodegradable polymers. It is a fact that these plastic food-packaging materials are disposable and non-biodegradable. Consequently, large amounts of plastic are accumulating in the terrestrial and aquatic ecosystems, hence various sectors like fishery, agriculture, hydroelectric power generation, marine transportation, health, and tourism are in danger. [11] With the ever-increasing concern of dumped petrochemical-based packaging wastes in the environment, green and sustainable materials are highly demanded to reduce the harmful effects of plastics on the environment. [12] Contrary to synthetic plastics, bio-based polymers decompose, degrade, return to the soil and decrease the volume of garbage. Biobased materials are derived from renewable and sustainable biomass. [12] Bio-based materials turn the bioplastics sector from a wasteful linear economy to a circular economy. [9] Biopolymers derived from bio-based materials are categorized into natural, semi-synthetic, and microbial polymers. [13] Polysaccharides, protein, lipids, polylactic acid, polyhydroxyalkanoate, pullulan, and xanthan gum are well-known bio-based materials due to their ability to form three-dimensional polymer networks. Polysaccharides are further categorized as starch, cellulose, lignin, K-carrageenan, alginate, pectin, and chitosan. Protein is grouped into gelatin, casein, caseinates, whey protein, soy protein isolate, wheat gluten, and corn zein. [14] Polymers produced by microorganisms are further classified as polyhydroxyalkanoate, pullulan, xanthan gum. [13] Polylactic acid is synthesized from lactic acid that is produced by microbes through lactide formation, then condensation polymerization and ring open polymerization. [15] Several studies indicated there is a great possibility of bio-based materials for developing eco-friendly fish packaging alternatives [16,17] This article aims to review the application of different biobased polymers embedded with bioactive molecules for fish packaging materials.

## Polysaccharides-based biopolymers for fish product packaging

The most widely used polysaccharide biopolymers in fish packaging are cellulose, chitin/ chitosan, starch, lignin, pectin, alginate, and K-Carrageenan. [18] In addition to food packaging, bio-based materials can be applied to the filtration of microbes, military security, and environmental management. Today numerous polysaccharides-based packaging materials have been developed for fish packaging materials (Table 1). Polysaccharides are easily modified to improve their physicochemical properties through heat gelatinization, pH changes, crosslinking, and hydrolysis. [19] Gases barrier, mechanical, thermal, and chemical properties of biomaterials are important criteria to select polysaccharides as packaging materials. [20] The water vapor, gas barrier, structural and mechanical properties of biopolymers can be improved by adding bioactive, nanofillers, cross-linkers, or plasticizers. [21] Polysaccharide-based packaging material has several advantages as compared to other biopolymers. It easily forms covalent or non-covalent interactions networks with other polymers. They are compatible with additives, which improves the functionality of polysaccharide-based film. [22]

Starch-based biopolymer is a widely accepted packaging film due to its availability in wide agricultural sources, ease of extraction, does not affect the sensory properties of food and can be edible without causing health risks to a human. [10] Bio-based materials extruded from starch conserves frozen pack fish fillets for 360 days better as compared to low-density



Table 1. Polysaccharides-based biopolymers for fish product packaging

Polysaccharides	Bioactive molecules	Applications	References
Rice starch	Oregano essential oil (OEO)	<ul> <li>Fish fillet packed in starch/OEO showed less oxidation and microbial growth</li> </ul>	[19,23]
Cassava starch	Citrus lemon peel extract (CLPE)	<ul> <li>Fish packaged in a film containing 20% CLPE demonstrated low peroxide and Total Volatile Basic Nitrogen (TVB-N) values</li> </ul>	[24]
Starch/Pectin	Feijoa extracts	<ul> <li>Antimicrobial against E. coli, Salmonella and Shigella.</li> <li>Increase the shelf life of perishable food</li> </ul>	[25]
Chitosan nanoparticles/ collagen protein	Anthocyanidin and Cinnamon-perilla essential oil	<ul> <li>Fillets of sea bream fillets wrapped in the composite film extended shelf life to 6–8 days</li> </ul>	[26]
Polycaprolactone Chitosan Rutin (PCL-CS-R)		<ul> <li>PCL-CS-R films decreased the microbial population of E. coli, S. aureus, and L. monocytogenes by 18.39%, 19.27%, and 17.45% as compared to polycaprolactone film alone in rainbow trout packaging</li> </ul>	[27]
Cellulose nanofiber /Carboxymethyl cellulose	Shikonin	<ul> <li>Discoloration of shikonin at weak acid and weak alkali to monitor fish freshness</li> </ul>	[28]
Pectin/Sodium alginate/Xanthan gum	Raspberry pomace extracts	<ul> <li>Changes its color (pH-sensitive) used to monitor protein-rich foods</li> </ul>	[29]
Pectin	Oregano essential oil, Ginger essential oil	<ul> <li>Significant protective effect on protein oxidation, prevention of endogenous enzyme activity</li> <li>Enhanced shelf life of yellow croaker for 7 days during ice storage.</li> </ul>	[30]
Pectin/Chitosan	Tarragon essential oil	Decreased bacterial deterioration of seafood during chilling	[31]
Chitosan	10% purple tomato anthocyanins	<ul> <li>Used to indicate the freshness of milk and fish/ monitoring food freshness/spoilage (intelligent film)</li> </ul>	[32]
Chitosan/ Methyl cellulose	Saffron petal anthocyanins	<ul> <li>Antimicrobial against E.coli and S.aureus, antioxidant activity, and monitor lamb meat freshness during storage (smart packaging)</li> </ul>	[33]
Chitosan/ Methyl celullose	Anthocyanin	<ul> <li>A potent antioxidant, antibacterial against (E. coli, P.aeroginos and S.aureus) and monitors fish fillet freshness at room tem- perature (smart packaging)</li> </ul>	[34]
Bacterial cellulose	Pelargonidin dye	<ul> <li>Monitors changes in total volatile base nitrogen (TVB-N) amounts of tilapia fillets stored at 4°C and 25°C</li> </ul>	[35]
Sodium alginate	Purple onion peel extract (POPE)	<ul> <li>POPE increased antioxidant activity, the thickness of the alginate-based films, extend the shelf life of foods with high water content and susceptible to lipid oxidation</li> </ul>	[36]
Sodium caseinate	1% TiO <sub>2,</sub> Rosemary Essential oil (REO)	<ul> <li>Exhibited antimicrobial by reducing the psychrotrophic bacteria count at the levels of 1% TiO<sub>2</sub> and 2% REO. Reduced lipid oxidation, and lipolysis of lamb meat during refrigerated sto- rage for 15 days</li> </ul>	[37]
<b>Κ</b> - Carrageenan	CuO, TiO <sub>2</sub>	<ul> <li>Good active food packaging films retained high-quality bananas (weight loss, firmness, and surface color)</li> </ul>	[38]
<b>Κ</b> - Carrageenan	Red cabbage extract (Brassica oleraceae)	<ul> <li>Helped to monitor freshness and quality of rainbow trout fillets (Oncorhynchus mykiss) because of color change when quality deteriorates</li> </ul>	[39]

polyethylene packaging. [40] The application of cellulose alone as packaging materials is challenging due to its hydrophilic and crystalline nature. However, the derivatives of cellulose like carboxymethyl cellulose, hydroxypropyl methylcellulose, or methylcellulose hydroxypropyl all have good film-making properties. [41] Packaging films made of CMC- tea waste and furcellaran inhibit the growth of microorganisms and accumulation of biogenic amine, hence extending the shelf-life of salmon fillets. [42] Cellulose has intelligent properties, i.e can visually indicate the condition of packaged food when loaded with other bioactive molecules. Cellulose when embedded with cyanidin-3-glucoside can act as intelligent packaging that can indicate the freshness of tilapia fillets stored at 4°C and 25°C. [43] Chitosan and other polymers increase the shelf life of fish and its products under chilling conditions. Accordingly, the film made from chitosan-alginate has increased the shelf life of catfish by 15 days during refrigeration. [44] The



chitosan and chitosan-alginate coatings are recommended for refrigerated storage of catfish fillets. Similarly, chitosan when combined with the Lactoperoxidase system increases the shelf life of fish burgers by 5 days [45] K- Carrageenan, alginate, and agar are widely used to develop coatings and films due to their gel-forming abilities. [46] Oregano essential oil (0.4%) added into pectin increases the shelf-life of yellow croaker from 20 to 27 days. [47]

## Protein-based biopolymers for fish product packaging

Protein-based polymers are helpful because they possess valuable characteristics for the production of food packaging materials. Proteins have been intensively studied as bio-based packaging materials due to their film-forming ability, UV-barrier properties, mechanical properties, transparency, and barrier properties against oxygen and carbon dioxide diffusion. [22] Gelatin, collagen, fish proteins, corn zein, wheat gluten, whey, and soy protein are widely accepted for film formation due to their nature to form intermolecular bonds. [48] Different proteins and other biopolymers-based fish packaging materials incorporated with different bioactive molecules are presented in Table 2.

Table 2. Proteins-based biopolymers for fish product packaging.

Proteins	Bioactive molecules loaded	Applications	References
Gelatin	Eugenol nanofiber and Polylactic acid	Excellent antimicrobial and antioxidant biode- gradable films	[49]
Gelatin/ Kappa- Carrageenan	Anthocyanin and TiO <sub>2</sub> nanoparticles	<ul> <li>Changes its color based on changes in pH, act as antimicrobial, antioxidant and monitors fish freshness during storage</li> </ul>	[50]
Fish gelatin	Haskap berries (Lonicera caerulea L.) extract (anthocyanins and phenolic acids as major extract)	<ul> <li>Fish gelatin containing 1% of haskap berries extract showed antioxidants and color change as a function of the pH of intelligent packaging to monitor the freshness of shrimp</li> </ul>	[51]
Gelatin/ Oxidized chitin nanocrystals	Black rice bran anthocyanins	<ul> <li>Antioxidant activity and have great potential in monitoring freshness of shrimp and hairtail (smart packaging), high protein foods</li> </ul>	[52]
Gelatin/Chitosan (carboxymethyl chitosan)	0.5 mg/mL squid maillard peptides	Retarded lipid oxidation and microbial growth of bluefin tuna	[53]
Gelatin/Chitosan	0.4% TiO <sub>2</sub> - Ag	<ul> <li>Improves antibacterial and UV barrier capability</li> </ul>	[54]
Gelatin/Chitosan	ε-Polylysine	<ul> <li>Effective controlled six foodborne pathogens (E. coli, K. pneumoniae, S. enteritidis, P. aeroginosa, S. aureus, and L. monocytogens)</li> </ul>	[55]
Gelatin	Curcumin, betanin and anthocyanin	<ul> <li>Demonstrated superior color retention as compared to curcumin and anthocyanins color change with pH change application for intelligent packaging to indicate freshness and quality of foodstuffs such as seafood products</li> </ul>	[56]
Soy Protein Isolate/Gelatin	Essential oils of <i>Zataria multiflora</i> and <i>Cinnamon zeylanicum</i>	<ul> <li>The population of S.aureus, B.cereus, S.typhimur- ium, L.monocytogens, and E.coli was diminished via the inclusion of 20% Zataria multiflora active food packaging, extended shelf life</li> </ul>	[57]
Gelatin	Dialdehyde kappa-carrageenan (DAK-car) Thymol-loaded zein nanoparticles (ZNP)	<ul> <li>Films containing a 1:2 ratio of gelatin films (GEL)/DAK- car and thymol-loaded zein 0.25 and 0.5 mg/mL of thymol have antioxidant and antimicrobial activity in active food packaging</li> </ul>	[58]
Whey protein isolate (WPI)	Emulsions and nanoemulsions of <i>Citrus</i> sinensis essential oil peel extract (CSEO)	The film preserves food against oxidation and microbial spoilage improving shelf life and quality of foodstuffs	[59]
Gelatin	Oxidized guar gum green tea extracts (0.5 and 1.0% w/v).	Antimicrobial against <i>S.aureus</i> , higher antioxidant activity due to the presence of green tea extract	[60]



Gelatin is one of the first biopolymer materials proposed to carry bioactive compounds. [18] The fillets of common carp when coated with gelatin have improved the qualitative and sensory characteristics of fillets as compared to polyethylene plastics during freeze storage. [61] Gelatin when combined with other biopolymers has some synergistic effects to control some foodborne bacterial pathogens. Gelatin-chitosan films enriched with rosemary essential oils have a great potential for controlling Salmonella enteric, Campylobacter jejuni, Pseudomonas aeruginosa, and Escherichia coli. [62] Soy protein isolates incorporated with nanoparticles (1% CuO and TiO2) decrease water vapor permeability of films, thus, can be applied as an active packaging system for different foodstuffs. [63] Coating of packaging materials with whey protein isolates exhibits high oxygen barrier properties and delayed peroxide formation of frozen shrimp fried rice during six months of frozen storage. [64] The addition of small amounts of chitosan in whey protein isolate creates a stronger network structure through complex coacervation, higher tensile strength, and lower water vapor permeability rate as compared to mono-component chitosan and whey protein isolate. [65] Due to its hydrophobic nature, Zein protein has low water vapor permeability and solubility. [14]

## Polylactic acid and polyhydroxyalkanoates-based biopolymers for fish product packaging

Polylactic acid (PLA) is synthesized from lactic acid monomers that can be widely used for fish packaging during chilling storage. [66] Polylactic acid, polyhydroxyalkanoates, pullulan, and xanthan gum are the most widely used microbial polymers for fish packaging (Table 3). The properties that make PHAs ideal for food packaging materials are stability in the air, nontoxicity, hydrophobicity, and pure enantiomer. [67]

## Integration of nanofillers into biopolymers

Nanofillers are nano-sized materials that maintain the microbiological safety of food, improve the mechanical, thermal, oxygen, and moisture barrier properties of bio-based packaging of meat, fruits, and seafood in active packaging. [78] Montmorillonite, nanofibers, nanowhiskers, silver, copper, zinc oxide, and Titanium dioxide are widely used nanofiller in active packaging Table 4.

## Integration of bioactive molecules into biopolymers

The incorporation of bioactive molecules improves the mechanical, barrier, antioxidant, and antimicrobial properties of polymers.<sup>[79]</sup> Bioactive molecules change their color based on changes in pH, temperature, light, time, and ammonia that making which acts as an indicator in monitoring the spoilage of packaged fish products. [8] Fish spoilage is usually monitored by identifying adenosine triphosphate decomposition, microbial plate counts, total volatile base nitrogen, lipid oxidation, and sensory properties. Monitoring the real-time freshness of fish using chemical, physical, biological, and sensory methods requires professional staff, tedious, complicated, time-consuming, and destructive. The emerging techniques use halochromic (pH-sensitive) bioactive molecules that enable consumers and non-specialists to understand the freshness conditions of fish using their naked eyes. [80]

Some of the pH-sensitive bioactive molecules (Table 5) are anthocyanins, betalains, carotenoids, carotenoids clove oil, curcumin, turmeric, rosemary, oregano, thyme, green tea, sage, basil, ginger, coriander, garlic, nutmeg, mace, savory and fennel. [81] The most intensively studied bioactive molecules as colorimetric indicators are anthocyanins, [82] curcumin, [83] and carotenoids. [84] Anthocyanins incorporated into biopolymer films have been used as smart indicators to monitor fish spoilage in Grass carp, [85] rainbow trout, [86] Hair-tail, Spade nose shark, [84] Pangasius, [87] and Atlantic mackerel. [88] The other widely used bioactive molecule is betalains. They are secondary nitrogencontaining metabolites of plants, water-soluble is responsible for yellow and orange to red-purple and

Table 3. The use of polylactic acids and polyhydroxyalkanoates-based biopolymers for fish product packaging.

Polymers	Bioactive molecules loaded	Role of the packaging films	References
Polylactic acid	Cinnamaldehyde/ Tea polyphenol	<ul> <li>Damaged the cell wall membrane leading to change in cell membrane permeability, protein synthesis, and expression of Shewanella putrefaciens fresh-keeping material with antibacterial properties</li> </ul>	[89]
Polylactic acid	Nanocellulose/ Chirosan	<ul> <li>Polylactic acid coated with nanocellulose/chitosan by showing the color change with spoilage progress has the notential to monitor sociate in heaf and other most product refrice radio at 4°</li> </ul>	[69]
Polylactic acid	ZnO	<ul> <li>Poly (lactic acid) (PLA)/ZnO nanocomposite films fabricated using ultra-high pressure has a great potential for food packaging with reduced permeability toward oxygen and water vapor</li> </ul>	[70]
Polylactic acid	Nanocellulose	<ul> <li>An Indian anchovy (Stolephorus indicus) fish packed in PLA/nanocellulose demonstrated increased shelf life as compared to neat PLA and LDPE during chilling storage for 20 days</li> </ul>	[12]
Polyactic acid (PLA) / Sawdust (SD) particles	Bacteriocin from Weissellahellenica BCC 7293 was diffusion coated onto PLA/SD	<ul> <li>Retarded the growth of Gram-positive (Listeria monocytogenes, Staphylococcus aureus) and Gram- negative bacteria (Pseudomonas aeruginosa, Aeromonas hydrophila, Escherichia coli, and Salmonella typhimurium) antimicrobial packaqinq for panqasius fish fillets</li> </ul>	[72]
Poly (butylene adipate co- terephthalate)–PBAT	Oregano ( <i>Origanum vulgare</i> ) essential oil (OEO)	<ul> <li>Revealed antibacterial activity (reduced growth of coliforms, Staphylococcus aureus, and psychrotrophic microorganisms) and prolonged storage quality of fish fillet for 10 days</li> </ul>	[73]
Poly lactic acid (PLA)-poly hydroxybutyrate (PHB	Cinnamaldehyde (5%)	<ul> <li>PLA-PHB films are active packaging films that can substitute plastic for chilled salmon storage and reduced the total bacterial counts of salmon dices</li> </ul>	[74]
Polybutylene adipate-co- terephthalate (PBAT)	Silver montmorillonite (Ag-MMT)	<ul> <li>PBAT/Ag-MMT reduced water and oxygen permeabilities, antibacterial and extended shelf life of sea bream for 15 days</li> </ul>	[75]
Pullulan and sodium carboxymethylcellulose (PUL–CMC)	Gallic acid (GA)/ Epsilon-poly-L-lysine (PL) hydrochloride	<ul> <li>Inhibit protein degradation, microbial growth and lipid oxidation of stored sea bass (Lateolabrax maculatus) fillet during storage at 4°C for 20 days (synergistic effect of GA and PL)</li> </ul>	[76]
Gellan gum (GM) heat-treated soy protein isolate (HSPI)	Clitoriaternatea (CT) extract	<ul> <li>Gellan gum improves the release of CT anthocyanins and HSPI regulated its release rate. The films have antimicrobial, antioxidant, and change of color on spoilage progress and hence help to monitor shrimp spoilage</li> </ul>	[77]

	_
	$\overline{}$
( -	(رڪ
1	-,

Nanofillers	<b>Embedded polymers</b>	Characteristics of nanofillers	Mechanisms of action of nanofillers	References
TiO <sub>2</sub> /Ag	Rhinobatoscemiculus gelatin	Antioxidant properties	<ul> <li>Embedding 4% TiO<sub>2</sub>-Ag nanoparticles into gelatin film gave good metal chelating and DPPH scavenging activity</li> </ul>	
TiO <sub>2</sub> /ZnO	4A-Zeolite Gelatin	Antimicrobial properties	<ul> <li>TiO<sub>2</sub> combined with ZnO disrupted the microbial cell membrane and emitted reactive oxygen species damaging phospholipids molecules in the cell membrane</li> </ul>	[94]
Se/ZnO	Gelatin/Cellulose nanofibers	Antioxidant and antimicrobial activity	<ul> <li>Antimicropial against Listeria monocytogenes &gt; Escherichia coli &gt; Staphylococcus aureus &gt; Pseudomonas fluorescens though releasing ions and catalysis the formation of active oxygen species</li> <li>Antioxidant through donating electrons from oxygen atoms of nanoparticles to nitrogen atoms odd electron in DPPH</li> </ul>	[92]
TiO <sub>2</sub>	Polylactic acidModified with Lycopene	Antimicrobial and antioxidant activity	<ul> <li>Due to lack of lipoprotein in the cell membranes, it can easily damage the cell wall and enter into the cell of gram-positive bacteria.</li> <li>Antimicrobial (Escherichia coli and Staphylococcus aureus) and antioxidant film with suitable color properties for active and intelligent packaging in food</li> </ul>	
ZnO	Chisosan/Melissa officinalis essential oil	Chisosan/Melissa officinalis Antimicrobial and antioxidant essential oil	<ul> <li>Due to the presence of a positive charge in chitosan polymer, citronellal and geraniol in Melisa essential oils increases the permeability of the cytoplasmic membrane to ATP which leads to cell death (antimicrobial biodegradable composite film for food packaging)</li> </ul>	
TiO <sub>2</sub>	Gelatin/Grape fruit extracts	Gelatin/Grape fruit extracts Antibacterial against E. coli, <i>L. monocytogens</i> and antioxidant	<ul> <li>Polyphenol and a-tocopherol cause cell death due to the accumulation of reactive oxygen species which leads to a change in the membrane permeability and alters metabolic mechanisms</li> <li>UV-barrier, antimicrobial (Escherichia coli and Listeria monocytogenes) and antioxidant activity</li> </ul>	
ZnO/SiO <sub>2</sub>	Chitosan	Antibacterial	<ul> <li>Mold growth of Escherichia coli, IRAQ 3and Staphylococcus aureus, S33Rhas been prevented via the inclusion of 5% ZnO-SiO2</li> </ul>	
TiO <sub>2</sub>	K-CarrageenanXanthan gumGillam gum	Antibacterial	<ul> <li>Protection from UV light, partial antimicrobial activity against Staphylococcus aureus</li> </ul>	[100]
ZnO	Polylactic acid	Antibacterial	<ul> <li>Exhibited antibacterial activity against Escherichia coli and Listeria monocytogenesduring storage of minced fish paste</li> <li>Exhibited UV-light and water vapor barrier properties</li> </ul>	
ZnO	Carboxymethyl celluloseGrape seed extract (5 wt%)	Antibacterial	<ul> <li>Zinc oxide nanoparticles increased water and mechanical properties</li> <li>Antibacterial against <i>Lmonocytogenes and Ecoli</i></li> <li>It preserves high fat meat products</li> <li>Less water vanor harrier and antioxidant activities</li> </ul>	[102]



 Table 5. The beneficial effect of incorporating bioactive compounds into various polymers.

Bioactive molecules	Embedded polymers	Benefits of bioactive molecules	Mechanisms of action of bioactive molecules	References
Echium amoenum anthocyanins	Bacterial cellulose film	Color change spotted to identify freshness/ spoilage of shrimp for fresh (violet), use soon (gray), and spoiled (yellow) shrimp	<ul> <li>As pH increases anthocyanin's structure changes from flavylium to quinoidal, eventually changing its color from blue-purple to green and yellow</li> </ul>	
Gallic acid Clove oil	Gelatin Chitosan	Gelatin-chitosan-gallic acid-clove oil prolonged the shelf life of sal- mon fillet for five days	<ul> <li>Better gas and oxygen barrier properties, inhibition of microbial growth, antioxidant effects of coating</li> </ul>	[104]
Oxidized chitin nanocrystals Curcumin	Chitosan	The color of the films was changed due to a change in pH which enabled identify spoilage of the hairtail and shrimp	<ul> <li>The mechanical, barrier against light and water vapor had been improved by curcumin – chitin nanocrystal incorporation in the film</li> </ul>	[105]
Betalains and phenolic compounds from amaranthus leaf extract	Gelatin	Enhanced the storage quality of fish/chicken from three days for control to 12 days foramaranthus leaf extract treated film	<ul> <li>Antioxidant, antimicrobial, and intelligent packaging (visible color change from red to yellow on spoilage)</li> </ul>	
Betacyanin	Glucomannan	<ul> <li>The film had changed its color from purple to yellow when TVB- N reached 39. 74 mg/ 100 g</li> </ul>	<ul> <li>Smart packaging during fish Osphronemusgouramystorage to monitor freshness</li> </ul>	[106]
Lyophilized alga Fucus spiralis powder	Gelatin	<ul> <li>The formation of FFA and growth of proteolytic, aerobes, and psy- chrotrophic bacteria had been impaired, increasing antimicrobial and antioxidant effects with increased alga in the film</li> </ul>	<ul> <li>The activity of oxidative phosphor- ylation and microbial enzyme had been inhibited</li> </ul>	[107]

Table 6. Essential properties of packaging improved due to immobilization of nanofillers/bioactive molecules into polymers.

Polymers/ bioactive molecules/ nanofillers	Properties of biocomposite packaging materials modified	Mechanisms of action of the packaging materials	References
Carboxymethyl- cellulose (CMC) Starch Purple sweet potato anthocyanins (PSPA)	<ul> <li>New interaction between cellulose and PSPA appeared</li> <li>PSPA was uniformly dispersed in CMC and Starch</li> <li>The addition of PSPA increased tensile strength, decreased elongation at break and moisture content</li> </ul>	<ul> <li>Changed its color from red to blue and is sensitive to ammonia</li> <li>Intelligent packaging to monitor fish freshness</li> </ul>	[85]
Starch Jackfruit seeds anthocyanins	Higher tensile strength, reduced resistance	<ul><li>Fish freshness indicator</li><li>Intelligent packaging</li></ul>	[108]
Starch Roselle anthocyanins	<ul> <li>Anthocyanins were immobilized into starch film, water content and tensile strength decreased, elongation at break increased</li> </ul>	<ul> <li>The film was sensitive to ammonia and monitors fish freshness at 4°C</li> <li>Intelligent packaging</li> </ul>	[109]
Bacterial nanocellulose Black carrot anthocyanins	Immobilization of black carrot anthocya- nins decreased the mean diameter of nanofibers	<ul> <li>Monitors the freshness of common carp and rainbow trout at 4°C.</li> <li>Consumers realize spoilage by the naked eye due to color changes Intelligent packaging</li> </ul>	[110]
Zein nanofibers Alizarin	<ul> <li>Alizarin is incorporated in to the zein matrix through hydrogen bonding</li> <li>Dehydration temperature, protein unfold- ing and glass transition reduced</li> </ul>	<ul> <li>Monitor the freshness of trout through changing its color in response to micro- bial and color changes</li> </ul>	[111]
Chitosan/ Xylan/ Hydroxyapatie/ Curcumin	Immobilization of curcumin into the polymers did not alter the surface of the film	<ul><li>Monitor freshness in Indian oil sardines</li><li>Smart packaging</li></ul>	[112]

#### Table 6. (Continued).

Polymers/ bioactive molecules/ nanofillers	Properties of biocomposite packaging materials modified	Mechanisms of action of the packaging materials	References
Bacterial cellulose Chitosan Curcumin	<ul> <li>Improved contact angles, mechanical properties, water vapor transmission, lower moisture content, and oxygen transmission rate</li> </ul>	Promising active packaging materials	[113]
Chitosan Rice berry phenolics extract	<ul> <li>Chitosan- rice berry phenolics extract films exhibited increased thermal stability, mechanical resistance, hydrophobicity, barrier, and antioxidant properties</li> </ul>	<ul> <li>The film changed its color from orange-red to yellow (naked eye detectable color changes) during shrimp spoilage monitoring</li> </ul>	[114]
ZnO Rosemary extract Anthocyanins Montmorillonite	<ul> <li>Showed remarkable antibacterial, antioxidant, and air barrier activity</li> </ul>		
Gelatin/Cellulose/ Arabic gum TiO <sub>2</sub> Garlic extract	<ul> <li>Enhanced the mechanical, antimicrobial, thermal, water vapor, and oxygen trans- mission rate</li> </ul>	<ul> <li>Bionanocomposite film synergistically con- trolled the growth of microbes during refrigeration of tilapia fillets</li> </ul>	[116]

violet colors. Based on its principal sources this pigment can be categorized into two broad types: betacyanins and betaxanthines. [89] Curcumin is also a known bioactive molecule found in the rhizome of turmeric (*Curcuma longa* L.) that can change its color when food loses its freshness. [90]

## Important properties of packaging materials

The most crucial properties of packaging materials are tensile strength, water vapor transmission rate, oxygen transmission rate, elongation at break, the thickness of the film, water-solubility, moisture content, mechanical properties, surface morphology, antioxidant and antibacterial properties. <sup>[91]</sup> The instruments used to characterize the properties of packaging materials are Fourier transform infrared spectroscopy, Scanning electron microscopy, Differential Scanning Calorimeter, X-Ray Diffraction. <sup>[92]</sup> The embedding of nanofillers, bioactive molecules, and essential oils into biopolymer improves the nature of packaging materials (Table 6).

## **Conclusion and future perspective**

Valorization of wasted food into useful packaging materials is the top agenda to avert the effect of synthetic plastics on the environment. Polysaccharides like cellulose, starch, chitosan or chitin, lignin, pectin, alginate, and carrageenan can be extracted from natural biomass. Similarly, proteins like gelatin, casein and caseinates, whey proteins, wheat gluten, soy protein isolate, and corn zein are easily isolated from plants and animals' sources. Polyhydroxyalkanoates, pullulan, and xanthan gum can be produced by microorganisms. All these biopolymers notably demonstrate excellent physicochemical, thermal, and mechanical properties when mixed or alone to be used as packaging materials. Some of the essential properties like morphological, thermal, gas barrier, water vapor permeability, antioxidant, and antibacterial of packaging films can be improved by immobilizing nanofillers or bioactive molecules. As a result, these biodegradable packaging materials can be applied as active, intelligent, or smart based on the types of natural pigment during fish packaging. These natural plant-based pigments are nontoxic and safe have antioxidant and antimicrobial properties, enhance shelf life, and enable monitoring of the freshness conditions of fish under storage conditions. Future research has to focus on the use of nanotechnology and smart sensors which allow communication information about the product to the consumers.



#### Disclosure statement

No potential conflict of interest was reported by the author(s).

#### References

- [1] Stankus, A. State of World Aquaculture 2020 and Regional Reviews: FAO Webinar Series. FAO Aquaculture Newsletter.2021, 20 (63), 17-18.
- [2] FAO.The State of World Fisheries and Aquaculture 2020. Sustainability in action.2020, Food and Agriculture Organization of United Nations, Rome, Italy.
- [3] Chan, C.Y.; Tran, N.; Cheong, K.C.; Sulser, T.B.; Cohen, P.J.; Wiebe, K.; Nasr-Allah, A.M. The future of fish in Africa: Employment and investment opportunities. PLoS ONE. 2021, 16, 1–21.
- [4] Maire, E.; Graham, N.A.J.; MacNeil, M.A.; Lam, V.W.Y.; Robinson, J.P.W.; Cheung, W.W.L.; Hicks, C.C. Micronutrient supply from global marine fisheries under climate change and overfishing. Curr. Biol.2021, 31 (18), 4132–4138.e3.
- [5] Sharmila, G.; Muthukumaran, C.; Kumar, N.M.; Sivakumar, V.M. Food waste valorization for biopolymer production. In Current Developments in Biotechnology and Bioengineering Sustainable Food Waste Management: Resource Recovery and Treatment. 1st; Wong, J., Kaur, G., Taherzadeh, M., Pandey, A., Lasaridi, K. Eds.; Elsevier: Amsterdam, Netherlands, 2020.
- [6] Vibha, C.; Parameswaranpillai, J.; Krishnasamy, S.; Siengchin, S.; Jayakumar, A.; Radoor, S.; Rangappa, S.; Salim, N.; Hameed, N.; Praveen, G.L. and Dominic, C.D. Biodegradable polymers and green-based antimicrobial packaging materials. In Biodegradable Polymers, Blends and Composites 1st edition (pp. 717-733); Sanjay, M.R., Parameswaranphilli, J., Siengchin, S., Ramesh. Eds.; Woodhead Publishing Series in Composites Science and Engineering: Bngkok, Thailand, 2021.
- [7] John, M.J.; Kennedy, J. Advanced polysaccharide based products from biomass resources. Int.J. Biol.Macromol. 2020, 151, 508. DOI: 10.1016/j.ijbiomac.2020.01.301.
- [8] Bhargava, N.; Sharanagat, V.; Mor, R.; Kumar, K. Active and intelligent biodegradable packaging films using food and food waste-derived bioactive compounds: A review. Trends Food Sci. Technol.2020,105, 385-401. DOI: 10.1016/j.tifs.2020.09.015.
- [9] Faisal, S. Naveed, M.; Kifayatullah, S.; Muhammad, M. Plastic Recycling for Energy Production. In Waste-to-Energy: Recent Developments and Future Perspectives towards Circular Economy 1st (pp. 411-447); Abomohra, A. E.F., Wang, Q., Huang. J Eds. Springer, Cham, 2022.
- [10] Sharma, N.; Bhardwaj, A.; Said, P.; Joshi, S.; Poonia, A.; Sahu, J.K. Scope, Functions, and Novelty of Packaging Edibles. In Edible Food Packaging 1st (pp. 87-101); Poonia, A., Dhewa, T. Springer, Singapore, 2020.
- [11] Mofijur, M.; Ahmed, S.F.; Rahman, S.M.A.; Arafat Siddiki, S.Y.; Islam, A.B.M.S.; Shahabuddin, M.; Ong, H.C.; Mahlia, T.M.I.; Djavanroodi, F.; Show, P.L. Source, distribution and emerging threat of micro- and nanoplastics to marine organism and human health: Socio-economic impact and management strategies. Environ. Res. 2021,195, 110857. DOI: 10.1016/j.envres.2021.110857.
- [12] Wang, J.; Euring, M.; Ostendorf, K.; Zhang, K. Biobased materials for food packaging. J. Bioresour. Bioprod. 2022, 7(1), 1–13, DOI 10.1016/j.jobab.2021.11.004.
- [13] Baranwal, J.; Barse, B.; Fais, A.; Delogu, G. L.; Kumar, A. Biopolymer: A Sustainable Material for Food and Medical Applications. Polymers. 2022, 14(5), 1–22.
- [14] Martins, V. G.; Romani, V. P.; Martins, P. C.; Nogueira, D. Protein-based materials for packaging applications. In Bio-based Packaging: Material, Environmental and Economic Aspects. Series edition (pp. 27-49); Sapuan, S.M., Ilyas, R.A., Stevens, C.V. Eds; John Wiley & Sons Ltd, 2021.
- [15] Ganguly, S.; Das, P. Synthesis and Production of Polylactic Acid (PLA). In Polylactic Acid-Based Nanocellulose and Cellulose Composites1st (pp. 29-51); Parameswaranpillai, J., Siengchin, S., Salim, N.V., George, J.J., Poulose, A. Eds.; CRC Press, Boca Raton, 2022.
- [16] Dogra, V.; Verma, D.; Fortunati, E. Biopolymers and nanomaterials in food packaging and applications. In Nanotechnology-Based Sustainable Alternatives for the Management of Plant Diseases 1st (pp. 355-374); Balestra, G.M., Fortunati, E. Eds; Elsevier, Amesterdam, Netherland, 2022.
- [17] Felicia, L.; Rovina, K.; Aqilah, N. N.; Vonnie, J. M.; Erna, K. H.; Misson, M.; Abdul Halid, N. Recent Advancements of Polysaccharides to Enhance Quality and Delay Ripening of Fresh Produce: A Review. Polymers. 2022, 14(7). DOI: 10.3390/polym14071341.
- [18] Nogueira, G. F.; de Oliveira, R. A.; Velasco, J. I.; Fakhouri, F. M. Methods of incorporating plant-derived bioactive compounds into films made with agro-based polymers for application as food packaging: A brief review. Polymers.2020, 12(11), 1-34. DOI: 10.3390/polym12112518.
- [19] Nešić, A.; Cabrera-Barjas, G.; Dimitrijević-Branković, S.; Davidović, S.; Radovanović, N.; Delattre, C. Prospect of polysaccharide-based materials as advanced food packaging. *Molecules*.2020, 25(1), 135.



- [20] Fonseca, J.; Koop, B. L.; Trevisol, T. C.; Capello, C., Monteiro, A. R.; Valencia, G. A. An Overview of Biopolymers in Food Packaging Systems. In Nanotechnology-Enhanced Food Packaging 1st (pp. 19-53); Parameswaranpillai, J., Radhakrishan, E.K., Aswathy, J., Sanjay, M.R., Suchart, S. Eds. Wiley-VCH, Weinhein, Germany, 2021.
- [21] Calderón-Santoyo, M.; Solis-Velazquez, O. A.; Ragazzo-Sánchez, J. A.; Iñiguez-Moreno, M. Animal-and Plant-Based Edible Food Packaging for Perishable Foodstuff. In Edible Food Packaging 1st (39-85); Poonia, A., Dhewa, T. Eds.; Springer, Singapore, 2020.
- [22] Roy, S.; Rhim, J. Anthocyanin food colorant and its application in pH-responsive color change indicator films change indicator films. Crit Rev Food Sci and Nutr. 2020, 1-29. DOI: 10.1080/10408398.2020.1776211.
- [23] Martins, P. C.; Bagatini, D. C.; Martins, V. G. Oregano essential oil addition in rice starch films and its effects on the chilled fish storage. J. Food Sci. Technol.2021, 58(4), 1562-1573. DOI: 10.1007/s13197-020-04668-z.
- [24] Oluwasina, O. O.; Awonyemi, I. O. Citrus Peel Extract Starch-Based Bioplastic: Effect of Extract Concentration on Packed Fish and Bioplastic Properties. J. Polym. Enviro. 2021, 29(6), 1706–1716. DOI: 10.1007/s10924-020-01990-7.
- [25] Sganzerla, W. G.; da Rosa, C. G.; da Silva, A. P. G.; Ferrareze, J. P.; Azevedo, M. S.; Forster-Carneiro, T.; Nunes, M. R.; de Lima Veeck, A. P. Application in situ of biodegradable films produced with starch, citric pectin and functionalized with feijoa (Acca sellowiana (Berg) Burret) extracts: An effective proposal for food conservation. Int.J.Biol.Macromol. 2021, 189, 544-553. DOI: 10.1016/j.ijbiomac.2021.08.146.
- [26] Zhao, R., Guan, W., Zheng, P., Tian, F., Zhang, Z., Sun, Z., Cai, L. Development of edible composite film based on chitosan nanoparticles and their application in packaging of fresh red sea bream fillets. Food Control. 2022, 132, 108545. DOI: 10.1016/j.foodcont.2021.108545.
- [27] Piri, H.; Moradi, S.; Amiri, R. The fabrication of a novel film based on polycaprolactone incorporated with chitosan and rutin: potential as an antibacterial carrier for rainbow trout packaging. Food Sci. Biotechnol. 2021, 30 (5), 683–690. DOI: 10.1007/s10068-021-00898-9.
- [28] Ezati, P.; Priyadarshi, R.; Bang, Y. J.; Rhim, J. W. CMC and CNF-based intelligent pH-responsive color indicator films integrated with shikonin to monitor fish freshness. Food Control. 2021, 126. DOI: 10.1016/j. foodcont.2021.108046.
- [29] Yang, J.; Fan, Y.; Cui, J.; Yang, L.; Su, H.; Yang, P.; Pan, J. Colorimetric films based on pectin/sodium alginate/ xanthan gum incorporated with raspberry pomace extract for monitoring protein-rich food freshness. Int. J. Biol. Macromol.2021, 185(3), 959-965. DOI:10.1016/j.ijbiomac.2021.06.198.
- [30] Lan, W.; Lang, A.; Chen, M.; Xie, J. Combined effects of pectin-plant essential oil coating with vacuum packaging on the quality of large yellow croaker (Pseudosciaena crocea) during iced storage. J Food Saf. 2022, e12960.
- [31] Esmaeili, M.; Khodanazary, A. Effects of pectin/chitosan composite and bi-layer coatings combined with Artemisia dracunculus essential oil on the mackerel's shelf life. J. Food Meas. Charact. 2021, 15(4), 3367-3375. DOI: 10.1007/s11694-021-00879-w.
- [32] Li, Y.; Wu, K.; Wang, B.; Li, X. Colorimetric indicator based on purple tomato anthocyanins and chitosan for application in intelligent packaging. Int.J.Biol.Macromol.2021, 174, 370-376. DOI: 10.1016/j. ijbiomac.2021.01.182.
- [33] Alizadeh-Sani, M.; Tavassoli, M.; McClements, D. J.; Hamishehkar, H. Multifunctional halochromic packaging materials: Saffron petal anthocyanin loaded-chitosan nanofiber/methyl cellulose matrices. Food Hydrocoll. 111, 2021(February 2021) 106237. DOI: 10.1016/j.foodhyd.2020.106237.
- [34] Gasti, T.; Dixit, S.; D'souza, O. J.; Hiremani, V. D.; Vootla, S. K.; Masti, S. P.; Chougale, R. B.; Malabadi, R. B. Smart biodegradable films based on chitosan/methylcellulose containing Phyllanthus reticulatus anthocyanin for monitoring the freshness of fish fillet. Int.J.Biol.Macromol.2021, 187, 451-461. DOI: 10.1016/j. ijbiomac.2021.07.128.
- [35] Liu, H.; Shi, C.; Sun, X.; Zhang, J.; Ji, Z. Intelligent colorimetric indicator film based on bacterial cellulose and pelargonidin dye to indicate the freshness of tilapia fillets. Food Packag. Shelf Life. 2021, 29, 100712. DOI: 10.1016/ j.fpsl.2021.100712.
- [36] Santos, L. G.; Silva, G. F. A.; Gomes, B. M.; Martins, V. G. A novel sodium alginate active films functionalized with purple onion peel extract (Allium cepa). Biocatal. Agric. Biotechnol. 2021, 35. DOI: 10.1016/j. bcab.2021.102096.
- [37] Alizadeh-Sani, M.; Mohammadian, E.; McClements, D. J. Eco-friendly active packaging consisting of nanostructured biopolymer matrix reinforced with TiO2 and essential oil: Application for preservation of refrigerated meat. Food Chem. 2020, 322, 126782. DOI: 10.1016/j.foodchem.2020.126782.
- [38] Ezati, P.; Riahi, Z.; Rhim, J. W. Carrageenan-Based Functional Films Integrated with CuO-Doped Titanium Nanotubes for Active Food-Packaging Applications. ACS Susstain. Chem. Eng. 2021, 9(28), 9300-9307. DOI: 10.1021/acssuschemeng.1c01957.
- [39] Rostamzad, H.; Kamali Sabeti, N.; Babakhani, A. Production and evaluation of smart biodegradable film based on carrageenan for fish fillet packaging. J. Fish.2019, 72(1), 85-95.
- [40] Cossa, M. de A. V.; Bilck, A. P.; Yamashita, F.; Mitterer-Daltoé, M. L. Biodegradable packaging as a suitable protectant for the conservation of frozen pacu (Piaractus mesopotamicus) for 360 days of storage at -18°C. J. Food *Process. and Preser.* 2022, 46(1), 1–11. DOI: 10.1111/jfpp.16133.



- [41] You, P.; Wang, L.; Zhou, N.; Yang, Y.; Pang, J. A pH-intelligent response fish packaging film: Konjac glucomannan/carboxymethyl cellulose/blackcurrant anthocyanin antibacterial composite film. Int.J.Biol.Macromol. 2022, 204, 386-396.
- [42] Jamróz, E.; Tkaczewska, J.; Kopeć, M.; Cholewa-Wójcik, A. Shelf-life extension of salmon using active total biodegradable packaging with tea ground waste and furcellaran-CMC double-layered films. Food Chem. 2022, 383, 132425. DOI: 10.1016/J.FOODCHEM.2022.132425.
- [43] Shi, C.; Ji, Z.; Zhang, J.; Jia, Z.; Yang, X. Preparation and characterization of intelligent packaging film for visual inspection of tilapia fillets freshness using cyanidin and bacterial cellulose. Int. J. Biol. Macromol. 2022, 205, 357-365. DOI: 10.1016/J.IJBIOMAC.2022.02.072.
- [44] Linn, N. C. C.; Waiprib, Y., Wilaipun, P. Shelf-life Extension of Refrigerated Hybrid Catfish (Clarias macrocephalus × Clarias gariepinus) Fillet by Chitosan- and Alginate-Based Edible Coatings. J. Fish. and Environ. 2021,
- [45] Ehsani, A.; Hashemi, M.; Afshari, A.; Aminzare, M.; Raeisi, M.; Zeinali, T. Effect of different types of active biodegradable films containing lactoperoxidase system or sage essential oil on the shelf life of fish burger during refrigerated storage. LWT. 2020, 117, 108633. DOI: 10.1016/j.lwt.2019.108633.
- [46] Jayakody, M. M.; Vanniarachchy, M. P. G.; Wijesekara, I. Seaweed derived alginate, agar, and carrageenan based edible coatings and films for the food industry: a review. J. Food Meas. Charact. 2022, 16, 1195-1227. DOI:10.1007/s11694-021-01277-y.
- [47] Lan, W.; Sun, Y.; Chen, M.; Li, H.; Ren, Z.; Lu, Z.; Xie, J. Effects of pectin combined with plant essential oils on water migration, myofibrillar proteins and muscle tissue enzyme activity of vacuum packaged large yellow croaker (Pseudosciaena crocea) during ice storage. Food Packag. Shelf Life. 2021, 30(December 2021), 100699. DOI:10.1016/j.fpsl.2021.100699.
- [48] Rajeshkumar, G.; Seshadri, S. A.; Richelle, R. R.; Mitha, K. M.; Abinaya, V. Production of biodegradable films and blends from proteins. In Biodegradable Polymers, Blends and Composites 1st edition; Sanjay, M.R., Parameswaranphilli, J., Siengchin, S., Ramesh. Eds.; Woodhead Publishing, Bngkok, Thailand, 2021.
- [49] Li, M.; Yu, H.; Xie, Y.; Guo, Y.; Cheng, Y.; Qian, H.; Yao, W. Fabrication of eugenol loaded gelatin nanofibers by electrospinning technique as active packaging material. LWT.2021, 139. DOI: 10.1016/j.lwt.2020.110800.
- [50] Sani, M.A.; Tavassoli, M.; Salim, S.A.; Azizi-lalabadi, M.; McClements, D.J. Development of green halochromic smart and active packaging materials: TiO2 nanoparticles and anthocyanin- loaded gelatin/K-carrageenan films. Food Hydrocoll. 2022, 124, 108324. DOI:10.1016/j.foodhyd.2021.107324.
- [51] Liu, J.; Yong, H.; Liu, Y.; Qin, Y.; Kan, J.; Liu, J. Preparation and characterization of active and intelligent films based on fish gelatin and haskap berries (Lonicera caerulea L.) extract. Food Packag. Shelf Life. 2019, 22, 100417. DOI: 10.1016/j.fpsl.2019.100417.
- [52] Ge, Y.; Li, Y.; Bai, Y.; Yuan, C.; Wu, C.; Hu, Y. Intelligent gelatin/oxidized chitin nanocrystals nanocomposite films containing black rice bran anthocyanins for fish freshness monitorings. Int.J.Biol.Macromol. 2020, 155, 1296–1306. DOI: 10.1016/j.ijbiomac.2019.11.101.
- [53] Jiang, W.; Hu, S.; Li, S.; Liu, Y. Evaluation of the preservation effect of gelatin-water soluble chitosan film incorporated with maillard peptides on bluefin tuna (Thunnus thynnus) slices packaging. LWT. 2019, 113, 108294. DOI: 10.1016/j.lwt.2019.108294.
- [54] Lin, D.; Yang, Y.; Wang, J.; Yan, W.; Wu, Z.; Chen, H.; Zhang, Q.; Wu, D.; Qin, W.; Tu, Z. Preparation and characterization of TiO2-Ag loaded fish gelatin-chitosan antibacterial composite film for food packaging. Int.J. Biol.Macromol.2020, 154, 123-133. DOI: 10.1016/j.ijbiomac.2020.03.070.
- [55] Liu, F.; Liu, Y.; Sun, Z.; Wang, D.; Wu, H.; Du, L.; Wang, D. Preparation and antibacterial properties of εpolylysine-containing gelatin/chitosan nanofiber films. Int. J. Biol. Macromol. 2020, 164, 3376-3387. DOI: 10.1016/ j.ijbiomac.2020.08.152.
- [56] Etxabide, A.; Maté, J. I.; Kilmartin, P. A. Effect of curcumin, betanin and anthocyanin containing colourants addition on gelatin films properties for intelligent films development. Food Hydrocoll. 2021, 115. DOI: 10.1016/j. foodhyd.2021.106593.
- [57] Raeisi, M.; Mohammadi, M. A.; Coban, O. E.; Ramezani, S.; Ghorbani, M.; Tabibiazar, M.; Khoshbakht, R.; Noori, S. M. A. Physicochemical and antibacterial effect of Soy Protein Isolate/Gelatin electrospun nanofibres incorporated with Zataria multiflora and Cinnamon zeylanicum essential oils. J. Food Meas. Charact. 2021, 15(2), 1116-1126. DOI: 10.1007/s11694-020-00700-0.
- [58] Yavari Maroufi, L.; Ghorbani, M.; Tabibiazar, M.; Mohammadi, M.; Pezeshki, A. Advanced properties of gelatin film by incorporating modified kappa-carrageenan and zein nanoparticles for active food packaging. Int. J. Biol. Macromol. 2021, 183, 753-759. DOI: 10.1016/j.ijbiomac. 2021.04.163.
- [59] Amjadi, S.; Almasi, H.; Ghadertaj, A.; Mehryar, L. Whey protein isolate-based films incorporated with nanoemulsions of orange peel (Citrus sinensis) essential oil: Preparation and characterization. J. Food Process. Pres. 2021, 45(2), 1-12. DOI: 10.1111/jfpp.15196.
- [60] Yavari Maroufi, L.; Ghorbani, M.; Tabibiazar, M. A Gelatin-Based Film Reinforced by Covalent Interaction with Oxidized Guar Gum Containing Green Tea Extract as an Active Food Packaging System. Food Bioprocess Technol. 2020, 13(9), 1633-1644. DOI: 10.1007/s11947-020-02509-7.



- [61] Hussein, A. A.; Ahme, M. M. The differences between glazing with solutions, coating with fish waste extracted gelatin and polyethylene-packaging of common carp fish fillets and their effects on qualitative and sensory characteristics during different freezing storage periods. *Journal of Kerbala for Agricultural Sciences*.2022, 9(1), 19–28.
- [62] Walid, Y.; Malgorzata, N.; Katarzyna, R.; Piotr, B.; Ewa, O. L.; Izabela, B.; Wissem, A. W.; Majdi, H.; Slim, J.; Karima, H. N.; Dorota, W. R.; Moufida, S. T. Effect of rosemary essential oil and ethanol extract on physicochemical and antibacterial properties of optimized gelatin-chitosan film using mixture design. *J. Food Process. Pre.* 2022, 46(1), e16059. DOI: 10.1111/JFPP.16059.
- [63] Roufegarinejad, L. Development and Characterization of the Reinforced Soy Protein Isolate-Based Nanocomposite Film with CuO and TiO<sub>2</sub> Nanoparticles. J. Polym. Environ. 2022, 69, 1–9. DOI: 10.1007/ s10924-022-02374-9.
- [64] Song, H.; Choi, I.; Lee, J. S.; Chang, Y.; Yoon, C. S.; Han, J. Whey protein isolate coating material for high oxygen barrier properties: A scale-up study from laboratory to industrial scale and its application to food packaging. *Food Packag. Shelf Life.* 2022, 31, 100765. DOI: 10.1016/J.FPSL.2021.100765.
- [65] Tavares, L.; Souza, H. K. S.; Gonçalves, M. P.; Rocha, C. M. R. Physicochemical and microstructural properties of composite edible film obtained by complex coacervation between chitosan and whey protein isolate. *Food Hydrocoll*. 2021, 113, 106471. DOI: 10.1016/J.FOODHYD.2020.106471.
- [66] Qin, D.; Bi, S.; You, X.; Wang, M.; Cong, X.; Yuan, C.; Yu, M.; Cheng, X.; Chen, X. G. Development and application of fish scale wastes as versatile natural biomaterials. *Chem. Eng. J.* 2022, 428, 131102. DOI: 10.1016/j. cej.2021.131102.
- [67] Yasim-Anuar, T.A.T.; Norrrahim, M.N.F.; Sapuan, S.M.; Ilyas, R.A.; Jenol, M.A.; Razali, N.A.M.; Hakimi, M.I.; Rahim, N.F.A.;Najmuddin, S.U.F.S. Polyhydroxyalkanoates for Packaging Application. In *Bio-based Packaging: Material, Environmental and Economic Aspects*. Series edition (pp. 279-293); Sapuan, S.M., Ilyas, R.A., Stevens, C. V. Eds; John Wiley & Sons Ltd, 2021.
- [68] Han, Y.; Ding, J.; Zhang, J.; Li, Q.; Yang, H.; Sun, T.; Li, H. Fabrication and characterization of polylactic acid coaxial antibacterial nanofibers embedded with cinnamaldehyde/tea polyphenol with food packaging potential. *Int.J.Biol.Macromol.* 2021, 184, 739–749. DOI: 10.1016/j.ijbiomac.2021.06.143.
- [69] Sobhan, A.; Muthukumarappan, K.; Wei, L.; Zhou, R.; Tummala, H. Development of a polylactic acid-coated nanocellulose/chitosan-based film indicator for real-time monitoring of beef spoilage. *Anal. Methods.* 2021, *13* (23), 2612–2623. DOI: 10.1039/d1ay00365h.
- [70] Cui, R.; Fan, C.; Dong, X.; Fang, K.; Li, L.; Qin, Y. Effect of ultrahigh-pressure treatment on the functional properties of poly(lactic acid)/ZnO nanocomposite food packaging film. *J.Sci.Food Agri.* 2021, 101(12), 4925– 4933. DOI: 10.1002/jsfa.11136.
- [71] Thomas, G.; Kumar, K. S.; Panda, S. K.; Bindu, J. Nanocellulose incorporated Polylactic Acid Films for chilled preservation of Indian Anchovy (Stolephorus indicus) (van Hasselt, 1823). Fishery Technology. 2021, 58, 104–112.
- [72] Woraprayote, W.; Pumpuang, L.; Tosukhowong, A.; Zendo, T.; Sonomoto, K.; Benjakul, S.; Visessanguan, W. Antimicrobial biodegradable food packaging impregnated with Bacteriocin 7293 for control of pathogenic bacteria in pangasius fish fillets. LWT Food Sci. Technol. 2018, 89, 427–433. DOI: 10.1016/j.lwt.2017.10.026.
- [73] Cardoso, L. G.; Pereira Santos, J. C.; Camilloto, G. P.; Miranda, A. L.; Druzian, J. I.; Guimarães, A. G. Development of active films poly (butylene adipate co-terephthalate) PBAT incorporated with oregano essential oil and application in fish fillet preservation. *Ind. Crops Prod.* 2017, 108, 388–397. DOI: 10.1016/j. indcrop.2017.06.058.
- [74] Ma, Y.; Li, L.; Wang, Y. Development of PLA-PHB-based biodegradable active packaging and its application to salmon. *Packag. Technol Sci.*2018, *31*(11), 739–746. DOI: 10.1002/pts.2408.
- [75] Seray, M.; Hadj-Hamou, A. S.; Uzunlu, S.; Benhacine, F. Development of active packaging films based on poly (butylene adipate-co-terephthalate) and silver-montmorillonite for shelf life extension of sea bream. *Polym. Bull.*2021, 0123456789. DOI: 10.1007/s00289-021-03671-4.
- [76] Li, Q.; Zhang, J.; Zhu, J.; Lin, H.; Sun, T.; Cheng, L. Effects of gallic acid combined with epsilon-polylysine hydrochloride incorporated in a pullulan-CMC edible coating on the storage quality of sea bass. RSC Adv.2021, 11(47), 29675–29683. DOI: 10.1039/d1ra02320a.
- [77] Wu, L. T.; Tsai, I. L.; Ho, Y. C.; Hang, Y. H.; Lin, C.; Tsai, M. L.; Mi, F. L. Active and intelligent gellan gum-based packaging films for controlling anthocyanins release and monitoring food freshness. *Carbohydr. Polym.* 2021, 254, 117410. DOI: 10.1016/j.carbpol.2020.117410.
- [78] Mahmud, J.; Sarmast, E.; Shankar, S.; Lacroix, M. Advantages of nanotechnology developments in active food packaging. Food Res. Int. 2022, 154, 111023. DOI: 10.1016/J.FOODRES.2022.111023.
- [79] Tavassoli, M.; Sani, M. A.; Khezerlou, A., Ehsani; A.; McClements, D. J. Multifunctional nanocomposite active packaging materials: Immobilization of quercetin, lactoferrin, and chitosan nanofiber particles in gelatin films. Food Hydrocoll. 2021, 118, 106747. DOI: 10.1016/j.foodhyd.2021.106747.
- [80] Ma, Q.; Lu, X.; Wang, W.; Hubbe, M. A.; Liu, Y.; Mu, J.; Wang, J.; Sun, J.; Rojas, O. J. Recent developments in colorimetric and optical indicators stimulated by volatile base nitrogen to monitor seafood freshness. *Food Packag. Shelf Life*.2021, 28, 100634. DOI: 10.1016/j.fpsl.2021.100634.



- [81] Bharti, S. K.; Pathak, V.; Alam, T.; Arya, A.; Basak, G.; Awasthi, M. G. Materiality of Edible Film Packaging in Muscle Foods: A Worthwhile Conception. J Package Technol Res. 2020, 4(1), 117-132. DOI: 10.1007/s41783-020-
- [82] Zhang, C.; Li, Y.; Wang, P.; Zhang, H. Electrospinning of nanofibers: Potentials and perspectives for active food packaging. Compr. Rev. Food Sci. Food Saf. 2020, 19(2), 479-502. DOI: 10.1111/1541-4337.12536.
- [83] Musso, Y. S.; Salgado, P. R.; Mauri, A. N. Smart edible films based on gelatin and curcumin. Food Hydrocoll. 2017, 66, 8-15. DOI: 10.1016/j.foodhyd.2016.11.007.
- [84] Kanatt, S. R. Development of active/intelligent food packaging film containing Amaranthus leaf extract for shelf life extension of chicken/fish during chilled storage. Food Packag. Shelf Life. 2020, 24, 100506. DOI: 10.1016/j. fpsl.2020.100506.
- [85] Jiang, G.; Hou, X.; Zeng, X.; Zhang, C.; Wu, H.; Shen, G.; Li, S.; Luo, Q.; Li, M.; Liu, X.; Chen, A.; Wang, Z.; Zhang, Z. Preparation and characterization of indicator films from carboxymethyl-cellulose/starch and purple sweet potato (Ipomoea batatas (L.) lam) anthocyanins for monitoring fish freshness. Int.J.Biol.Macromol.2020, 143, 359-372. DOI: 10.1016/j.ijbiomac.2019.12.024.
- [86] Amiri, R.; Piri, H.; Akbari, M.; Moradi, G. The fabrication and kinetic modeling of a new time-temperature label based on paraffin wax and black carrot anthocyanin for monitoring fish products. Anal. Methods. 2020, 12(4), 544-551. DOI: 10.1039/c9ay02410g.
- [87] Matche, R. S.; Anup, G. J.; Mrudula, G. Development of Biodegradable Films from Marine Ingredients Incorporated with Natural Antimicrobial Agents for Food Packaging. J Package TechnolRes. 2020, 4(1), 45-55. DOI 10.1007/s41783-020-00085-x.
- [88] Jamróz, E.; Kulawik, P.; Guzik, P.; Duda, I. The verification of intelligent properties of furcellaran films with plant extracts on the stored fresh Atlantic mackerel during storage at 2°C. Food Hydrocoll. 2019, 97, 105211. DOI: 10.1016/j.foodhyd.2019.105211.
- [89] Carreón-Hidalgo, J. P.; Franco-Vásquez, D. C.; Gómez-Linton, D. R.; Pérez-Flores, L. J. Betalain plant sources, biosynthesis, extraction, stability enhancement methods, bioactivity, and applications. Food Res. Int. 2022, 151, 110821.
- [90] Priyadarshi, R.; Ezati, P.; Rhim, J.-W. Recent Advances in Intelligent Food Packaging Applications Using Natural Food Colorants. ACS Food Sci. Technol. 2021, 1(2), 124-138. DOI: 10.1021/acsfoodscitech.0c00039.
- [91] Yong, H.; Liu, J. Recent advances in the preparation, physical and functional properties, and applications of anthocyanins-based active and intelligent packaging films. Food Packag. Shelf Life. 2020, 26, 100550. DOI: 10.1016/j.fpsl.2020.100550.
- [92] Tomoda, B. T.; Yassue-Cordeiro, P. H.; Ernesto, J. V.; Lopes, P. S.; Péres, L. O.; da Silva, C. F.; de Moraes, M. A. Characterization of biopolymer membranes and films: Physicochemical, mechanical, barrier, and biological properties. In Biopolymer Membranes and Films: Health, Food, Environment, and Energy Applications 1st (pp. 97-95); De Moraes, M.A., Da Silva, C.F., Veira, R.S. Eds.; Elevier: Radarweg, Amsterdam, Netherlands, 2020.
- [93] Boughriba, S.; Souissi, N.; Jridi, M.; Li, S.; Nasri, M. Thermal, mechanical and microstructural characterization and antioxidant potential of Rhinobatos cemiculus gelatin films supplemented by titanium dioxide doped silver nanoparticles. Food Hydrocoll. 2020, 103, 105695. DOI: 10.1016/j.foodhyd.2020.105695.
- [94] Azizi-Lalabadi, M.; Alizadeh-Sani; M., Divband, B.; Ehsani, A.; McClements, D. J. Nanocomposite films consisting of functional nanoparticles (TiO2 and ZnO) embedded in 4A-Zeolite and mixed polymer matrices (gelatin and polyvinyl alcohol). Food Res. Int. 2020, 137, 109716. DOI: 10.1016/j.foodres.2020.109716.
- [95] Ahmadi, A.; Ahmadi, P.; Sani, M. A.; Ehsani, A.; Ghanbarzadeh, B. Functional biocompatible nanocomposite films consisting of selenium and zinc oxide nanoparticles embedded in gelatin/cellulose nanofiber matrices. Int.J. Biol.Macromol.2021, 175, 87-97. DOI: 10.1016/j.ijbiomac.2021.01.135.
- [96] Asadi, S.; Pirsa, S. Production of Biodegradable Film Based on Polylactic Acid, Modified with Lycopene Pigment and TiO<sub>2</sub> and Studying Its Physicochemical Properties. J. Polym Environ. 2020, 28(2), 433-444. DOI: 10.1007/ s10924-019-01618-5.
- [97] Sani, I. K.; Pirsa, S.; Tağı, Ş. Preparation of chitosan/zinc oxide/Melissa officinalis essential oil nano-composite film and evaluation of physical, mechanical and antimicrobial properties by response surface method. Polym. Test. 2019, 79. DOI: 10.1016/j.polymertesting.2019.106004.
- [98] Riahi, Z.; Priyadarshi, R.; Rhim, J. W.; Bagheri, R. Gelatin-based functional films integrated with grapefruit seed extract and TiO2 for active food packaging applications. Food Hydrocoll. 2021, 112, 106314. DOI:10.1016/j. foodhyd.2020.106314.
- [99] Al-Tayyar, N. A.; Youssef, A. M.; Al-Hindi, R. R. Antimicrobial packaging efficiency of ZnO-SiO2 nanocomposites infused into PVA/CS film for enhancing the shelf life of food products. Food Packag. Shelf Life. 2020, 25, 100523. DOI: 10.1016/j.fpsl.2020.100523.
- [100] Balasubramanian, R.; Kim, S. S.; Lee, J.; Lee, J. Effect of TiO2 on highly elastic, stretchable UV protective nanocomposite films formed by using a combination of k-Carrageenan, xanthan gum and gellan gum. Int.J. Biol.Macromol. 2019, 123, 1020-1027. DOI: 10.1016/j.ijbiomac.2018.11.151.



- [101] Shankar, S., Wang, L. F., & Rhim, J. W. (2018). Incorporation of zinc oxide nanoparticles improved the mechanical, water vapor barrier, UV-light barrier, and antibacterial properties of PLA-based nanocomposite films. Materials Science and Engineering C, 93(July), 289-298.
- [102] Priyadarshi, R.; Kim, S. M.; Rhim, J. W. Carboxymethyl cellulose-based multifunctional film combined with zinc oxide nanoparticles and grape seed extract for the preservation of high-fat meat products. Sustain. Mater. Technol.2021, 29, e00325. DOI: 10.1016/j.susmat.2021.e00325.
- [103] Mohammadalinejhad, S.; Almasi, H.; Moradi, M. Immobilization of Echium amoenum anthocyanins into bacterial cellulose film: A novel colorimetric pH indicator for freshness/spoilage monitoring of shrimp. Food Control. 2020, 113, 107169. DOI: 10.1016/j.foodcont.2020.107169.
- [104] Xiong, Y.; Kamboj, M.; Ajlouni, S.; Fang, Z. Incorporation of salmon bone gelatine with chitosan, gallic acid and clove oil as edible coating for the cold storage of fresh salmon fillet. Food Control. 2021, 125, 107994. DOI: 10.1016/j.foodcont.2021.107994.
- [105] Wu, C.; Sun, J.; Chen, M.; Ge, Y.; Ma, J.; Hu, Y.; Pang, J.; Yan, Z. Effect of oxidized chitin nanocrystals and curcumin into chitosan films for seafood freshness monitoring. Food Hydrocoll.2019, 95, 308-317. DOI: 10.1016/ j.foodhyd.2019.04.047.
- [106] Ardiyansyah, A. M. W.; Wahyono, A.; Fatoni, M.; Poerwanto, B.; Suryaningsih, W. The Potency of betacyanins extract from a peel of dragon fruits as a source of colourimetric indicator to develop intelligent packaging for fish freshness monitoring. IOP Conf. Ser. Earth Environ. Sci. 2018, 207(1). DOI: 10.1088/1755-1315/207/1/012038.
- [107] Trigo, M.; Nozal, P.; Miranda, J. M.; Aubourg, S. P.; Barros-Velázquez, J. Antimicrobial and antioxidant effect of lyophilized Fucus spiralis addition on gelatin film during refrigerated storage of mackerel. Food Control. 2022, 131. DOI: 10.1016/j.foodcont.2021.108416.
- [108] da COSTA, L. A.; Diógenes, I. C. N.; Oliveira, M. de A.; Ribeiro, S. F.; Furtado, R. F.; Bastos, M. D. S. R.; Silva, M. A. S.; Benevides, S. D. Smart film of jackfruit seed starch as a potential indicator of fish freshness. Food Sci. Technol (Campinas).2021, 41(2), 489-496. DOI: 10.1590/fst.06420.
- [109] Zhai, X.; Li, Z.; Zhang, J.; Shi, J.; Zou, X.; Huang, X.; Zhang, D.; Sun, Y.; Yang, Z.; Holmes, M.; Gong, Y.; Povey, M. Natural Biomaterial-Based Edible and pH-Sensitive Films Combined with Electrochemical Writing for Intelligent Food Packaging. J. Agric. Food Chem. 2018, 66(48), 12836-12846. DOI: 10.1021/acs.jafc.8b04932.
- [110] Moradi, M.; Tajik, H.; Almasi, H.; Forough, M.; Ezati, P. A novel pH-sensing indicator based on bacterial cellulose nanofibers and black carrot anthocyanins for monitoring fish freshness. Carbohydr. Polym. 2019, 222, 115030. DOI: 10.1016/j.carbpol.2019.115030.
- [111] Aghaei, Z.; Ghorani, B.; Emadzadeh, B.; Kadkhodaee, R.; Tucker, N. Protein-based halochromic electrospun nanosensor for monitoring trout fish freshness. Food Control.2020, 111, 107065. DOI: 10.1016/j. foodcont.2019.107065.
- [112] Vadivel, M.; Sankarganesh, M.; Raja, J. D.; Rajesh, J.; Mohanasundaram, D.; Alagar, M. Bioactive constituents and bio-waste derived chitosan / xylan based biodegradable hybrid nanocomposite for sensitive detection of fish freshness. Food Packag. Shelf Life. 2019, 22, 100384. DOI:10.1016/j.fpsl.2019.100384.
- [113] Xu, Y.; Liu, X.; Jiang, Q.; Yu, D.; Xu, Y.; Wang, B.; Xia, W. Development and properties of bacterial cellulose, curcumin, and chitosan composite biodegradable films for active packaging materials. Carbohydr. Polym. 2021, 260, 117778. DOI: 10.1016/j.carbpol.2021.117778.
- [114] Eze, F. N.; Jayeoye, T. J.; Singh, S. Fabrication of intelligent pH-sensing films with antioxidant potential for monitoring shrimp freshness via the fortification of chitosan matrix with broken Riceberry phenolic extract. Food Chem.2022, 366, 130574. DOI:10.1016/j.foodchem.2021.130574.
- [115] Eskandarabadi, S. M.; Mahmoudian, M., Farah; K. R., Abdali, A.; Nozad, E.; Enayati, M. Active intelligent packaging film based on ethylene vinyl acetate nanocomposite containing extracted anthocyanin, rosemary extract and ZnO/Fe-MMT nanoparticles. Food Packag. Shelf Life.2019, 22, 100389. DOI: 10.1016/j. fpsl.2019.100389.
- [116] Youssef, A. M.; El-Sayed, H. S.; El-Nagar, I.; El-Sayed, S. M. Preparation and characterization of novel bionanocomposites based on garlic extract for preserving fresh Nile tilapia fish fillets. RSC Adv. 2021, 11(37), 22571-22584. DOI:10.1039/d1ra03819b.